













Salt Spray Test Report ZC-704-05/A

Date of filling: August 15, 2022	Report date: August 24, 2022
Continuous spray time	Experimental requirements:
Start: 9:00 on August 15, 2022	≥ 120H, corrosion area ≤ 5%
End: 9:00 on August 24, 2022	

Test conditions:

1. Test temperature: 35 ± 2 °C	4. Brine concentration: 5%
2. Spray pressure: 1 ± 0.1kgf/cm2	5. PH value: 6.5-7.2
3. Pressure barrel temperature: 47 ± 2 °C	6. Spray collection: 1.0-2.0ml/80cm2/h

Serial No	Production line	Sample model	Sample surface coating	Determine	Remarks
1	Paint shop	BAR10277	NOF Geomet	Grade 8	Approve

Time	24 hours		
Pictures of test process			
Time	48 hours		
Pictures of test process			
Time	72 hours		
Pictures of test process			
Time	96 hours		
Pictures of test process			
Time	120 hours		
Pictures of test process	